



CREATING A CLEANER, SAFER, HEALTHIER WORLD.

COATINGS



ReVue™

ReVue™ -SLM | ReVue™ -CRM

CONCRETE MORTAR SYSTEMS

■ ReVue™ -SLM: Self-Leveling Mortar

Used as a general purpose underlayment which leaves a finished surface, that can withstand temporary construction traffic and is ideal for floor toppings

■ ReVue™ -CRM: Concrete Repair Mortar

Used to repair damaged concrete and to slope floors



T20

PHYSICAL/PERFORMANCE PROPERTIES

ReVue™-SLM PROPERTIES

Test Method	Results
VOC	0 g/L (0.0 lb/gal)
Compressive Strength (28 days)	5000 psi (41 MPa)
Flexural Strength (28 days)	1200psi (8 MPa)
Working Time	Approx. 30 minutes
Set Time	1-2 Hours
Hard Dry Time	8-24 hours minimum thickness at 70° F (21° C)

APPLICATION CHARACTERISTICS

Rates	
Thickness	1/8" to 1 1/2" (3.18 mm to 38 mm)
Coverage rate per bag mix	47 ft ² @ 1/8" (4.27 m ² @ 3.18 mm)
Yield per 50 lb. bag (22.7 kg bag)	0.47 cu ft. at 1/8" thickness

ReVue™-CRM PROPERTIES

Results	Slant Shear Bond	Direct Shear Bond
VOC (ASTM D3960)	0 g/L (0.0 lb/gal)	--
Working Time	20 minutes	--
Set Time	30-45 minutes	--
Open to Traffic	4 hours	--
Strength	3 hours = 1200 psi	--
--	1 day = 4500 psi	1,900
--	7 days = 6000 psi	2,900
--	28 days = 7000 psi	3,300
Freeze & Thaw Resistance (%RDM)	97	445
Rapid Chloride Permeability	1050 (low)	

APPLICATION CHARACTERISTICS

Rates	
Thickness	1/4" to 4" (6.35 mm to 101.6 mm)
Coverage rate per bag mix	9.6 ft ² @ 1/2" (0.89 m ² @ 12.7 mm)

Testing performed at ambient conditions unless stated otherwise.
Specifications subject to change without notice.



Tennant Company is a world leader in indoor and outdoor environmental cleaning solutions and floor and wall coatings.

USES:

ReVue™-SLM

Excels at leveling large areas. Works with a variety of surfaces such as concrete, well-bonded abraded mortars and ceramic tiles.

Can be prepared for the installation of carpet, resilient floors, wood parquet, slate, ceramic tile, marble, granite or stone veneer floors.

Properly prepared exterior grade plywood, cement board, anti-fracture membranes, insulating panels and other approved board underlayments may be covered.

ReVue™-CRM

Warehouses, vertical repairs, truck docks, heavy industrial repairs, commercial floors and ramps.

Can withstand extreme temperatures and is ideal for fast track projects in high traffic areas including streets and truck docks.

FOR FIRST IMPRESSIONS THAT LAST™

For additional information, call +1.800.228.4943

or email coatings@tennantco.com

2.042.001.am.en

ReVue™-SLM/CRM 4/18

©2017 The Tennant Company logo and other trademarks designated with the symbol "™" are trademarks of Tennant Company registered in the United States and/or other countries unless otherwise indicated. Tennant Company's products are sold and serviced through subsidiaries of Tennant Company and distributors. All rights reserved.

Tennant
701 North Lilac Drive
Minneapolis, MN 55422 USA

USA/Canada: +1.800.228.4943

www.tennantcoatings.com
coatings@tennantco.com